

Product Description

8159



Appcom compound

Modified PP Compound Injection Moulding Grade

Product Description : APPCOM 8159 COLOUR, 40% Mineral filled PP compound modified an other suitable additives to suit end applications. This grade has superior flow properties.

Colour : This grade is available as per customer requirement.

Application Area : The major application area is in the field of injection molding.

	Properties	Test Method	Condition	Unit	Specs value
Physical	Melt Flow Index	ASTM D1238	230°C/2.16 kg	gm/10min	Min 18
	Specific Gravity	ASTM D 792	23°C	-	1.20
Mechanical	Tensile Strength at yield (Type I, Speed 50 mm/min)	ASTM D638	23°C	kg _f /cm ²	Min 270
	Elongation at break (Type I, Speed 50 mm/min)	ASTM D638	23°C	%	Min 5
	Flexural Modulus (127*12.7*3.2 mm)	ASTM D790	23°C	kg _f /cm ²	Min 35000
	Izod Impact (notched)	ASTM D 256	23°C	Kj/m ²	Min 5
Thermal	HDT @1.8 Mpa (127*12.7*12.7 mm)	ASTM D648	23°C	°C	Min 65

- Variations within normal tolerances are possible for various colours. All values are measured atleast 48 hours storage at 23°C/ 50% relative humidity

Note: Please contact APPL for shrinkage recommendations.

Processing Guideline:

The injection temperature profile for above grade should be between 190°C to 230°C and the mould temperatures between 40°C to 60°C. We recommended that the pellet should be dried for about 1 - 2 hours at 75°C - 100°C to avoid moisture linked problem during processing.

Note: All the information given by APPL for use of these materials is given in good faith and to the best of our knowledge. The data, information, suggestion contained herein are given purely as guide. APPL does not guarantee the exact replication of the data by users since plastic testing is affected by a number of extraneous factors.

APPL Industries Ltd. Unit II - 680/2 Koregaon Bhima, Pune nagar road ,Pune –Maharashtra, India – 412 216
Telephone –02137 –253195 /196 Telefax –02137 253196 Email-aalekhpune@vsnl.net ,applindus@vsnl.net

Unit I - Plot No. - 2, Sector – 7, Industrial Estate, IMT Manesar, Gurgaon, Haryana, India – 122050
Telefax No 0124-2290740/741/742, Phone No 0124-3950622 E-Mail: applmsr@airtelbroadband.in