

# Product Description

## G2 CC



Appcom compound

## Glass Filled PP Compound Injection Moulding / Extrusion Grade

**Product Description** : APPCOM G2CC, 20% Glass filled chemically coupled polypropylene compound modified with other suitable additives to suit end applications.

**Colour** : This grade is available as per customer requirement.

**Application Area** : The major application area is in the field of Injection moulding / Extrusion.

	Properties	Test Method	Condition	Unit	Specs Value
<b>Physical</b>	Specific Gravity	ASTM D 792	23°C	--	1.04 ± 0.01
	Melt Flow Index	ASTM D1238	230°C/2.16 kg	gm/10min	4 ± 1
<b>Mechanical</b>	Tensile Strength at yield	ASTM D638	23°C	kg/cm <sup>2</sup>	750 ± 50
	Elongation at break	ASTM D638	23°C	%	Min 6
	Flexural Modulus	ASTM D790	23°C	kg/cm <sup>2</sup>	40000 ± 10%
	Izod Impact (notched)	ASTM D256	23°C	kg.cm/cm	10 ± 2
<b>Thermal</b>	HDT @4.6 kg/cm <sup>2</sup>	ASTM D648	23°C	°C	150 ± 3

\* Typical values only. Variations within normal tolerances are possible for various colours. All values are measured atleast 48 hours storage at 23°C/ 50% relative humidity

- Variations within normal tolerances are possible for various colours. All values are measured atleast 48 hours storage at 23°C/ 50% relative humidity

*Note:* Please contact APPL for shrinkage recommendations.

### Processing Guideline:

The injection temperature profile for above grade should be between 190°C to 230°C and the mould temperatures between 40°C to 60°C. We recommended that the pellet should be dried for about 1 - 2 hours at 75°C - 100°C to avoid moisture linked problem during processing.

**Note:** All the information given by APPL for use of these materials is given in good faith and to the best of our knowledge. The data, information, suggestion contained herein are given purely as guide. APPL does not guarantee the exact replication of the data by users since plastic testing is affected by a number of extraneous factors.

**APPL Industries Ltd.** Unit II - 680/2 Koregaon Bhima, Pune nagar road ,Pune –Maharashtra, India – 412 216  
Telephone –02137 –253195 /196 Telefax –02137 253196 [Email-aalekhpune@vsnl.net](mailto:Email-aalekhpune@vsnl.net) ,applindus@vsnl.net

Unit I - Plot No. - 2, Sector – 7, Industrial Estate, IMT Manesar, Gurgaon, Haryana, India – 122050  
Telefax No 0124-2290740/741/742, Phone No 0124-3950622 E-Mail: [applmsr@airtelbroadband.in](mailto:applmsr@airtelbroadband.in)